

## Ready Mix –Fluorescent Paint



### DESCRIPTION AND PROPERTIES

- FT Metallic Aluminium is a metallic aluminium cellulose enamel. Satin finish for painting industrial applications. Fast drying and high covering power.
- FT Metallic Aluminium does not comply with Directive 2004/42/EC, Annex II B, so it shall only be applied to coatings not included in such directive or in installations which comply with Directive 1999/13/EC.

### PHYSICAL CHARACTERISTICS



<b>Nature:</b>	Nitrosynthetic	
<b>Colour:</b>	Metal	
<b>Appearance:</b>	Gloss	
<b>Specific Weight:</b>	1.05-1.15kg/l at 20°C	
<b>Dry film thick:</b>	40 microns	2 coats
<b>Yield:</b>	12-15 m <sup>2</sup> /l	
<b>VOC:</b>	788 g/l	
<b>Solid content:</b>	12%	

### SURFACE PREPARATION








PROCESS			Paint OEM	Primer
	P360		✓	✓
	Panel Wipe		✓	✓

## APPLICATION

### MIXING RATIO

FT METALLIC ALUMINIUM		
<b>Panel Wipe</b>	100:150 volume	20" F/4 at 20°C

### APPLICATION METHOD

	 mm	 bar	 cm		
	1,3-1,5	3-3,5	15 - 20	2	5'
	1,3-1,5	3-3,5	15 - 20		
 HVLP	1,3-1,5	3-3,5	10		

## EQUIPMENT CLEANING

- Clean with a cleaning thinner.

## SAFETY

- Follow instructions of product label.
- For more information check the Safety Data Sheet.
- Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal

## STORAGE

- Store the product in a ventilated place far from direct exposure to sunlight.
- Keep between +5°C and +30°C.

## STORAGE

- In unopened original packaging, one year from manufacturing date.

For any technical information contact with our Customer Attention Service or our Technical Department. FT Paints declines any responsibility due to an incorrect use of the product.